

# ProSpec® Medium Bed PermaFlex® 300

Floor Preparation • Concrete Repair • Tile Setting

## 1. PRODUCT NAME

ProSpec® Medium Bed PermaFlex® 300

## 2. MANUFACTURER

H.B. Fuller Construction Products Inc.  
1105 South Frontenac Street  
Aurora, IL 60504-6451 U.S.A.

1-800-552-6225 Office  
1-800-952-2368 Fax  
prospec.com

## 3. PRODUCT DESCRIPTION

ProSpec® Medium Bed PermaFlex® 300 is an economical, one-component, portland cement-based, porcelain tile mortar designed for interior and exterior floor applications of large format tile (LFT) over concrete where the embedded thickness is between 3/16" - 3/4" (5 mm - 19 mm).

### Features and Benefits

- Polymer-modified, just add water
- Can be used for bedding thickness 3/16" - 3/4" (5 mm - 19 mm)
- Helps overcome irregularities in tile thickness
- Good workability
- Interior or exterior concrete floor applications only
- ANSI A118.4 and ISO 13007 C2

### Uses

#### For installation of:

- Porcelain tile
- Ceramic tile
- Quarry tile
- Non-moisture sensitive natural stone\*
- Cement tile and pavers
- High bottom lugged tile
- Ideal for light colored glass tile

\* All natural stone should be tested to be sure discoloration does not occur.

#### For installation over:

- Properly cured and finished concrete
- Cured portland cement mortar
- Cement backer unit (CBU)

Note: For other substrates, contact the ProSpec® Technical Services.

Note: Difficult to bond substrates like existing vinyl tile or cutback adhesive require extra preparation. Consult ProSpec® Technical Services.

## SAFETY

READ THE SAFETY DATA SHEET (SDS) BEFORE USING THIS PRODUCT. SDS Sheets are available on our website [prospec.com](http://prospec.com) or contact Medical Emergency Phone Number (24 Hours): 1-888-853-1758, Transport Emergency Phone Number (CHEMTREC): 1-800-424-9300 or contact ProSpec® Technical Services at 1-800-832-9023 (7:00AM to 5:00PM M-F, Central US Time).

## CAUTIONS

Read complete cautionary information printed on product container prior to use. For medical emergency information, call 1-888-853-1758.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about and guidelines for the proper use and application of the covered ProSpec® brand product(s) under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

## 4. TECHNICAL DATA

ProSpec® Medium Bed PermaFlex® 300	Time	Typical Values	ANSI A118.4
Shear Strength to Glazed Tile	7 days dry	> 390 psi (2.7 MPa)	> 300 psi (2.1 MPa)
Shear Strength to Porcelain Mosaic Tile	28 days dry	> 330 psi (2.3 MPa)	> 200 psi (1.3 MPa)
Shear Strength to Quarry Tile	28 days dry	> 380 psi (2.6 MPa)	> 150 psi (1.0 MPa)

Greater than: > Greater than or equal to: ≥ Less than: < Less than or equal to: ≤

Note: Test results obtained under controlled laboratory conditions at 72°F (22°C) and 50% relative humidity. Tested using 5.27 qt (5 L) water per 50 lb (23 kg) bag. Reasonable variations can occur due to atmospheric and job site conditions.

### LEED® Eligibility<sup>1</sup>

- Regional Materials (MR-c5)
- Low-Emitting Materials (IEQ-c4.1, IEQ-c4.3, IEQ-c4.6)

### Packaging

Gray: 50 lb (22.7 kg) bag - Product #65300479

White: 50 lb (22.7 kg) bag - Product #65300481

### Shelf Life

12 months from the date of manufacture when stored in the original, unopened container, away from moisture, under cool, dry conditions and out of direct sunlight.

## 5. INSTALLATION

### Preparation

- Surface must be clean, dry, hard and free from dirt, loose particles, wax, sealers, curing compounds, grease, paint, efflorescence and any foreign materials that will inhibit adhesion.
- Walls and floors must be structurally sound, free of movement and dimensionally stable.
- Surfaces to receive tile shall be plumb and true with square corners. Maximum variation from the required plane shall be: Subfloor Surfaces – 1/4" (6 mm) in 10' (3 m) for tile less than 15" (381 mm) on any one side and the required plane shall be 1/8" (3 mm) in 10' (3 m) for tile 15" (381 mm) or greater on any one side.
- Concrete floors must be fully cured (28 days) and have a fine broom finish. Sprinkle water on the substrate in various areas looking for penetration. If water droplet or beading of water is noticed then surface contaminants are present that will cause loss of adhesion and must be removed. Smooth troweled surfaces should be scarified to assure bond. Inspect surfaces that will receive the tile and the tools used to install it.

Notify the architect or other designated authority in writing of any defects or conditions that prevent a satisfactory tile installation. (See ANSI A108.5)

In case of truing or leveling the work of others, use ProSpec® Floor Patch Pro, a ProSpec® Level Set® Self-Leveling Underlayment or ProSpec® Vinyl Concrete Patch.

Expansion joints are necessary for all installations. Expansion joints shall be located (**refer to: TCNA Handbook for Ceramic Tile Installation Detail EJ171**):

- Where tile work abuts restraining surfaces, such as perimeter walls, curbs, columns, pipes and the like.
- Directly over joints in structural floors and over construction or cold joints.
- Directly over expansion or control joints.
- Where specified in the architectural drawing.
- All materials should be stored at 40°F - 80°F (4°C - 27°C) 24 hours prior to installation.

Note: It is the responsibility of the installer/applicator to ensure the suitability of the product for its intended use.

### Job Mockups

The manufacturer requires that when its ProSpec® products are used in any application or as part of any system that includes other manufacturers' products, the contractor and/or design professional shall test all the system components collectively for compatibility, performance and long-term intended use in accordance with pertinent and accepted industry standards prior to any construction. Written documentation of the tests performed shall be satisfactory to the design professional and contractor. Test results must include the means and methods of application, products used, project-specific conditions being addressed, and standardized tests performed for each proposed system or variation.

### Mixing

1. Use cool, clean potable water. Always use clean tools and mixing containers. Do not add latex additive.
2. Add just enough dry powder to the water to produce a thick but trowelable consistency (5 - 6 qt (4.7 - 5.7 L)) per 50 lb (22.7 kg). Too much water will cause the mortar to have reduced strength. Troweled ridges should not flow or slump.
3. Mix thoroughly. Let stand 10 minutes to give all ingredients time to slake. Remix and use. Do not add more water or powder after slaking is complete. This causes shrinkage and results in poor bond.
4. Do not mix with a high-speed power mixer. High speed mixing tends to beat in air and reduce the strength of the mortar.
5. The bucket life is approximately 2 - 3 hours, warmer temperatures will reduce bucket life.

Note: It is the responsibility of the installer/applicator to ensure the suitability of the product for its intended use.

### Application

Apply only to surfaces that are frost free and above 40°F (4°C) and below 100°F (38°C) within 24 hours of application and 72 hours thereafter. Installation must conform to the current specifications in ANSI A108.5 and the TCNA Handbook for Ceramic Tile Installations.

1. The proper trowel to be used with ProSpec® Medium Bed PermaFlex® 300 is a 19/32" (15 mm) notch trowel. The proper trowel should also result in a minimum of 80% coverage for interior or dry areas and 95% for exterior, wet areas or when placing natural stone.
2. Use only for direct bond adhesive applications.
3. Required when setting tiles > 15" (381 mm) on any one side and where the final embedded thickness will exceed 3/16" (5 mm) under the stone or tile.
4. With pressure, apply a skim coat to the substrate with the flat edge of the trowel.
5. Comb the mortar in one direction, with the recommended notched trowel. Apply mortar only on sections that can receive tile before skinning. If skinning occurs, scrape and discard skinned mortar.
6. Press tile into place and slide perpendicular to the combed ridges to insure proper coverage.
7. Final bond coat thickness must be between 3/16" - 3/4" (5 mm - 19 mm) after the tile is embedded.
8. Tile may be adjusted up to 15 minutes after placing.
9. Tile must be firmly set before grouting. This requires at least 16 - 24 hours. At cooler temperatures set times will be extended.
10. Grout with ProSpec® ProColor Sanded Grout, ProSpec® ProColor Unsanded Grout or ProSpec® B-7000 Epoxy Mortar & Grout.
11. Clean all tools with soapy water before mortar dries.

## Limitations

- Do not add latex.
- Do not expose to freezing conditions during the first 72 hours of curing.
- Do not adjust tile after mortar takes its initial set or the bond will be permanently broken.
- Do not soak tile.
- Do not use worn trowels. It is important to have the ridges of the tile setting mortar the full depth of the trowel notches.
- Do not allow traffic on freshly installed tile for 24 hours.
- Do not allow heavy traffic until 72 hours after installation.
- Do not use over masonite, particle board, luan, plastic, vinyl asbestos tile or painted surfaces.
- Do not use over wood.
- Do not use to level floors.

## Coverage

Coverage per 50 lb (22.7 kg) bag:

Medium Bed PermaFlex® 300 Notch Trowel Size	Approximate Coverage
1/2" x 1/2" x 1/2" Notch Trowel (13 mm x 13 mm x 13 mm)	36 - 45 ft <sup>2</sup> (3.3 - 4.2 m <sup>2</sup> )
19/32" (15 mm) Half moon trowel	25 - 30 ft <sup>2</sup> (2.3 - 2.8 m <sup>2</sup> )

Note: It is the responsibility of the installer/applicator to ensure the suitability of the product for its intended use.

## 6. AVAILABILITY

To locate ProSpec® products in your area, please contact:

Phone: 800-832-9002

Website: [prospec.com](http://prospec.com)

## 7. WARRANTY

For warranty details, see your sales associate or [prospec.com](http://prospec.com)

## 8. MAINTENANCE

Not applicable

## 9. TECHNICAL SERVICES

### Technical Assistance

Information is available by calling the Technical Support Hotline.

Toll Free: 800-832-9023

Fax: 630-952-1235

### Technical and safety literature

To acquire technical and safety literature, please

visit our website at [prospec.com](http://prospec.com)

## 10. FILING SYSTEM

Division 9

<sup>1</sup> ProSpec® products can contribute to LEED® credits within the Material Resource, (Recycled Content & Regional Materials) and Indoor Environmental Quality (Low Emitting Materials).

©Copyright 2014  
H.B. Fuller Construction Products Inc.

ProSpec®, PermaFlex® and  
Level Set® are trademarks of  
H.B. Fuller Construction Products Inc.

LEED® is a registered trademark of  
U.S. Green Building Council.

Data Sheets are subject to change  
without notice. For the latest revision,  
check our website at [prospec.com](http://prospec.com)



H.B. Fuller Construction Products Inc.

1105 South Frontenac Street  
Aurora, IL 60504-6451 U.S.A.  
[prospec.com](http://prospec.com)